



מפרטי מוצרים

(1)		
2 :	15.09.2013 :	S017 :'

ASTM D 4052	870.0	---	" / "	" 15 -
ASTM D 86	---	90	%	" 357 -
ASTM D 93	---	55	"	
IP 309	-2	---	"	(2) , ' ,CFPP
IP 336	0.10	---	%	
ASTM D 130	1	---	" 100 -	3 ,
ASTM D 445	6.0	2.5	" 40-	
ASTM D 4530	0.2	---	%	10% ,
ASTM D 974			----	
ASTM D 482	0.01	---	%	
ASTM D 6304	500	---	" / "	
ASTM D 473	0.01	---	%	
		10,000	" / "	(3)
			----	(4)

(1) " 107 2 (2005) .

(2) - 1- 15

(3) 6.2 " 107 :2

$$Q(H) = (52.190 - 8.802d^2 * 10^{-6}) [1 - 0.01*(x+y+s)] + 9.420*(0.01s)$$

= Q(H) :

(" ") " 15 - = d

(%) = x

(%) = s

(%) = y

.238.85 " "

(4)